

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 718 384 A2

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication:
26.06.1996 Bulletin 1996/26

(51) Int. Cl.⁶: C09D 11/10, G11B 7/26,
B41M 5/00

(21) Application number: 95203564.0

(22) Date of filing: 19.12.1995

(84) Designated Contracting States:
DE FR GB

(30) Priority: 22.12.1994 US 362364

(71) Applicant: EASTMAN KODAK COMPANY
Rochester, New York 14650-2201 (US)

(72) Inventors:
• Krencseski, Mary A.,
c/o Eastman Kodak Co.
Rochester, New York 14650-2201 (US)
• Swallow, Kevin J.,
c/o Eastman Kodak Co.
Rochester, New York 14650-2201 (US)

• Bugner, Douglas E.,
c/o Eastman Kodak Co.
Rochester, New York 14650-2201 (US)
• Amell, Alfred J.,
c/o Eastman Kodak Co.
Rochester, New York 14650-2201 (US)

(74) Representative: Haile, Helen Cynthia et al
Kodak Limited
Patent Department
Headstone Drive
Harrow, Middlesex HA1 4TY (GB)

(54) Screen-printable ink-receptive compositions

(57) This invention is a screen-printable ink receptive composition. It contains (a) a hydrophilic polymer and (b) a thickener and has (c) a viscosity of 10 to 1,000 poise at shear rates less than 10^0 s^{-1} and exhibits (d) a shear-thinning behavior defined by the following relationship:

$$\log(\text{viscosity}) = A [\log(\text{shear rate})]$$

wherein A represents (e) the slope of the line obtained by plotting $\log(\text{viscosity})$ against $\log(\text{shear rate})$ and has (f) a value of up to -0.1 when calculated over shear rates ranging from 10^0 to 10^{-2} s^{-1} .




FIGURE 1

EP 0 718 384 A2

Description

This invention relates to screen-printable ink-receptive coating compositions for use on substrates such as optical recording elements, particularly writable Photo CD elements.

5 Compact discs (CDs) are optical recording elements capable of storing large amounts of digital information. CDs are commonly used for storing audio information, video information, still images, documents, computer programs, and the like.

Consumer and commercial users alike have found writable CDs to be an outstanding medium for archival keeping of large volumes of data. It is critical that the CDs are protected against accidental data loss due to physical marring or
10 tampering with the surface. Eastman Kodak Company has provided users with a writable CD. This CD has a durable ultraviolet-cured crosslinked polyacrylate coating on the top (or back) surface opposite the optical readable surface. A user can write on this surface with a felt-tipped pen or even apply a pressure sensitive adhesive label to mark the CD with identifying bar codes or labels. Attempts to remove such a label or add another over it could cause an imbalance in the spinning of the CD during playback or recording. In the worse case such attempts could remove the information
15 recording layer and data from the CD.

There are numerous methods currently employed to label the back sides of CDs. When large numbers of CDs containing substantially the same digital information are mass-produced, labeling methods such as transfer lithography or silk-screening are commonly employed. However, when only one or even a few CDs are produced which contain unique information, these methods are economically unattractive.

20 Recently, a method of labeling CDs was disclosed which employs a drop-on-demand (DOD) ink jet mechanism to custom label CDs (*The Hardcopy Observer*, p 22, January, 1994). This method allows relatively rapid custom labeling of CDs using a black ink jet printing mechanism coupled to a computer. The label is composed using appropriate software on the computer and is then printed directly onto the surface of the CD.

Although this method of labeling allows for more economical custom labeling of CDs than traditional methods, such as transfer lithography, it requires that the surface of the back side of the CD be ink-receptive. It is also desirable for the
25 back side of the CD to be coated with protective, durable layers, such as those described in US-A-5,312,663. A preferred way of applying such durable overcoats to the back side of CDs is by screen-printing ultraviolet (UV) curable inks or lacquers. Unfortunately, the types of compositions which are useful as protective layers have been found to be unreceptive to common water-based ink jet inks, such as those used in the commercially available printer described above.

30 In European Patent Application 0 574 860 A2 ink-receptive layers are described which can be coated on the back side of CDs. However, the preferred ink-receptive layers of EP 0 564 860 A2 are not readily amenable to screen-printing methods because they do not possess the necessary rheological properties. They also do not provide the level of durability of the UV-curable compositions described in US-A-5,312,663.

Inventors have found that ink-receptive compositions known in the prior art for use in ink jet recording processes
35 generally possess rheological properties which are incompatible with the screen-printing process. For example, ink-receptive formulations such as those described in US-A-5,147,717 have a tendency to leak through the screen and/or flow over the outside edges of the screen frame. Such formulations are also prone to foaming during the printing process. Also, upon removal of the screen from a CD during printing, the coated formulation tends to be pulled along with the screen, forming strings or filaments of the coated formulation.

40 Figure 1 describes the relationship of viscosity and shear rate in the compositions of the invention.

We have found that by proper adjustment of the rheological properties the above problems are substantially solved. Accordingly the present invention provides a screen-printable ink receptive composition which contains (a) a hydrophilic polymer and (b) a thickener and has (c) a viscosity of 10 to 1,000 poise at shear rates less than 10^2 s^{-1} and exhibits (d) a shear-thinning behavior defined by the following relationship:

45

$$\log(\text{viscosity}) = A [\log(\text{shear rate})]$$

wherein A represents (e) the slope of the line obtained by plotting $\log(\text{viscosity})$ against $\log(\text{shear rate})$ and has (f) a value of up to -0.1 when calculated over shear rates ranging from 10^0 to 10^2 s^{-1} .

50 This composition is unexpectedly useful for screen-printing. Those skilled in the silk screen printing arts do not expect aqueous compositions to be screen-printable. Furthermore, these compositions are screen-printable over the durable, protective overcoats referred to above thereby retaining many of the desirable protective properties of such overcoats while providing at the same time an ink-receptive surface without having to invest in additional, costly coating or printing equipment.

55 The composition is applied to a substrate such as the surface of a CD by a method of screen-printing an ink-receptive composition on a substrate comprising the steps of:

- (a) providing a screen-printable ink receptive composition as defined above;
- (b) coating a fine meshed fabric screen with the composition provided in (a);

- (c) placing the coated fabric screen over the substrate;
- (d) filling the screen openings with the composition by passing an applicator over the surface of the fabric; and
- (e) forcing the composition onto the surface of the substrate as a coating by passing an applicator under pressure over the surface of the fabric.

5

Increasing the viscosity of the above mentioned prior art ink-receptive compositions by simply increasing the overall concentration of the non-volatile components solves the problem of the fluid leaking through the screen. However, the composition then does not readily pass through the screen upon application during the coating step, resulting in an incomplete coating and/or plugging of the screen openings. This appears to be due to the fact that the prior art compositions referred to under Background tend to be Newtonian. By Newtonian, we mean a fluid which exhibits constant viscosity as a function of shear rate. In these prior art compositions, it starts out at relatively high viscosity, and remains highly viscous even when the applicator is applied.

10

Figure 1 displays the relationship between shear rate and viscosity as a function of the steps in the screen-printing process for a typical commercial screen-printing ink, as further described by R. E. Trease and R. L. Dietz in *Solid State Technology*, January, 1972, pp 39-43. The salient features of the process represented in Figure 1 are as follows:

15

- a relatively high viscosity is preferred in the initial, low-shear-rate stage of the process, such that the screen-printable composition does not readily leak through the openings in the screen prior to the application of the applicator;
- a relatively low viscosity is preferred during the high-shear-rate step of passing the squeegee over the screen, such that the screen-printable composition passes freely through the openings of the screen; and
- the screen-printable composition returns to its high viscosity state shortly after the applicator is disengaged (return to the low-shear-rate regime), again such that the screen-printable composition does not leak through the screen.

20

Another way of characterizing a suitable screen-printable composition is that it should possess at least a minimum viscosity at low shear rates, and that it be shear-thinning or pseudoplastic, that is, it exhibits a decreasing viscosity as the shear rate increases. This satisfies the equation

25

$$\log(\text{viscosity}) = A[\log(\text{shear rate})]$$

wherein the coefficient A is up to -0.1 when calculated for shear rates ranging from 10^0 to 10^2 s^{-1} .

We have unexpectedly found that the addition of thickeners of a certain type to the above prior art ink-receptive compositions results in compositions which are shear-thinning. Through further experimentation, we have found that by adding a preferred amount of a preferred thickener so as to impart the desired degree of shear-thinning behavior and by adjusting the coating composition to overall higher solids concentration to yield the desired viscosity at low shear rates, usable screen-printable ink-receptive compositions can be prepared.

30

To achieve the desired rheological requirements as defined above, the concentration of solids in the screen-printable coating composition should range between 10 and 60 wt %, preferably between 30 and 40 wt %. This of course will vary somewhat depending upon the exact composition.

35

Useful screen-printable ink-receptive compositions can be formulated from hydrophilic polymer compositions comprising:

40

- (i) a poly(vinyl pyrrolidone);
- (ii) particles of a polyester ionomer, such as poly(cyclohexylenedimethylene-co-xylylene terephthalate-co-malonate-co-sodioiminobis(sulfonylbenzoate)); and
- (iii) a polyvinyl alcohol.

45

Preferred formulations are free of silicone-based oils or similar additives which are not cross-linked and which tend to reside at the surface of the coating. It has been found that such materials have a deleterious effect on the ink-receptivity of the subsequently coated screen-printable ink-receptive compositions.

50

The thickener is important in providing the combination of high viscosity at low shear rates and relatively low viscosity at high shear rates. There are many commercially available thickeners which may be useful for this purpose, for example polysaccharides, such as carrageenan, pectin, xanthan, starch amylose, gum arabic, guar gum, carboxymethylcellulose and other cellulose derivatives, and the like; ethylene oxide polymers; and vinyl ether polymers and copolymers, such as poly(methyl vinyl ether-co-maleic anhydride), poly(isobutyl vinyl ether-co-vinyl chloride), and butyl monoesters and other alkyl monoesters. Cellulose derivatives such as hydroxypropyl cellulose, hydroxypropylmethyl cellulose, hydroxyethyl cellulose, hydroxyethylmethyl cellulose, and carboxymethyl cellulose are also useful. Hydroxyethyl cellulose derivatives include those sold under the tradenames Natrosol by Aqualon, Inc. Natrosol 250 HBR is a high molecular weight

55

hydroxyethyl cellulose. The concentration of thickener will depend on the particular components in the screen-printable composition. Generally 0.1 to about 3 wt % will be sufficient although concentrations outside of this range may be useful depending on the other components. When Natrosol 250 HBR is used, its concentration should fall between 0.5 and 3 wt %, preferably between 1.5 and 2.5 wt %. One skilled in the art of factorial experiments would be able to determine the appropriate thickener, and concentration thereof, for a particular hydrophilic polymer composition to achieve the required rheological properties.

To overcome "stringiness", we found that a lower molecular weight version of poly(vinyl pyrrolidone) may be used, with no adverse consequences. The preferred weight average molecular weight of the poly(vinyl pyrrolidone) should be less than about 500,000, preferably in the range of 10,000 to 100,000. Poly(vinyl pyrrolidone) having a molecular weight of about 33,000 (PVP K-30) is used in the examples.

It is desirable to overcome formation of air bubbles in the coating during the screen-printing process. There are many commercially available defoamers which are designed to reduce or eliminate the problem of air entrainment. Examples of known antifoaming agents include acetylenic glycols, silicone fluids and emulsions, ethoxylated or propoxylated silicones, hydrocarbons, and fatty acid ester derivatives, acetylated polyamides, and poly(alkylene oxide) polymers and copolymers. In the following examples we used a silicone-free material sold under the tradename Surfynol D-75 by Air Products and Chemicals, Inc. A useful concentration range for the defoamer is from 0.01 to 1.0 wt %, preferably from 0.01 to 0.15 wt % or most preferably from 0.05 to 0.15 wt %.

Other useful additives may be added to improve surface characteristics such as texture and gloss. For example, surfactants may be used to control coating quality and inert particles may be used to control gloss. In practice, the gloss level of the surface of the coated CD is controlled by a combination of the screen mesh and the addition of inert particles. Useful inert particles include poly(methyl methacrylate-co-divinylbenzene) beads with an average particle diameter ranging from 3 to about 30 μm and at a concentration ranging from 0.5 to 5 wt % of the dried coating. Beads with an average diameter of 10 to 20 μm and at a concentration ranging from 0.5 to 2 wt % were used in the examples.

The screen-printable ink-receptive composition of the invention is screen-printed onto the CD over a silicone-free durable overcoat using either a manual process in which a screen is mounted in a wooden frame and an applicator, such as a squeegee is moved by hand or on an Autoroll Rotoflex 560 Compact Disc Printer equipped with multiple screen printing stations and a moving turntable that has nest pads capable of holding 35 CDs. The squeegee is moved at 32 in/s (81 cm/s) and the pressure is adjustable. Screen mesh size ranges from 110 to 470 threads per inch (43 to 185 threads per cm) are useful.

In both screen-printing techniques, using multiple passes, it is desirable to employ infrared lamps to dry the coating on the CD prior to additional applications.

The thickness of the screen printed ink-receptive layer is between 2 and 20 μm , preferably between 5 and 15 μm . The thickness is controlled by a combination of the rheology of the coating composition and the mesh size of the screen used in the screen-printing process.

The thickness of the ink receiving layer is critical to the quality of the ink jet print. In order to get a sufficiently thick layer on the CD surface it may be necessary to subject the CD to multiple passes in the screen printing process. Each pass should be followed by several seconds under an infrared heat lamp. This serves to drive off the moisture in the formulation and help smooth out any surface texture remaining from the screen.

The following examples illustrate the utility of the invention as screen-printable ink receptive compositions.

Example 1. An ink-receptive composition comprising 22 wt % poly[1,4-cyclohexylenedimethylene-co-2,2'-oxydiethylene (46/54) isophthalate-co-5-sodiosulfo-1,3-benzenedicarboxylate (82/18)] (obtained from Eastman Chemicals as AQ-55), 10.6 wt % poly(vinyl pyrrolidone) (PVP K-30 from International Specialty Products), 0.2 wt % poly(vinyl alcohol) (Airvol 350 from Air Products, Inc.), 1.5 wt % poly(methyl methacrylate-co-divinylbenzene) particles (average particle size: 15 μm , prepared by the Polymer Development Group at Eastman Kodak Co.), 0.1 wt % DF-75 (defoamer, from Air Products, Inc.), 2.0 wt % Natrosol 250 HBR (thickener, from Aqualon, Inc.), and 64 wt % distilled water was screen-printed over a recordable 120-mm diameter CD comprising a polycarbonate substrate, a recordable dye layer, an evaporated gold layer, a spin-coated first protective "lacquer layer", and a second protective durable overcoat layer (according to US-A-5, 312,663) comprising an ultraviolet curable composition known as RB343 SPL 3700 (provided by Naz-DAR/KC, Inc.) which was screen-printed using a 390 mesh screen and cured to a final thickness of approximately 7 μm . The ink-receptive coating was dried by brief exposure to infrared heat lamps, yielding a high quality 10 μm thick layer.

The writable CD as just described, bearing the screen printed ink-receptive coatings was labeled using a Trace CDP-5300 compact CD printer, and was found to exhibit good image quality, dry time, and durability.

Example 2. An ink-receptive composition comprising 14.1 wt % poly[1,4-cyclohexylenedimethylene-co-2,2'-oxydiethylene (46/54) isophthalate-co-5-sodiosulfo-1,3-benzenedicarboxylate (82/18)] (obtained from Eastman Chemicals as AQ-55), 6.0 wt % poly(vinyl pyrrolidone) (PVP K-30 from International Specialty Products), 0.2 wt % poly(vinyl alcohol) (Airvol 350 from Air Products, Inc.), 1.5 wt % poly(methyl methacrylate-co-divinylbenzene) particles (average particle size: 15 μm , prepared by the Polymer Development Group at Eastman Kodak Co.), 0.1 wt % DF-75 (defoamer, from Air Products, Inc.), 3.0 wt % Natrosol 99-250 H (thickener, from Aqualon, Inc.), and 75 wt % distilled water was screen-printed over a writable 120-mm diameter CD in the same manner as previously described in Example 1.

The writable CD as just described was labeled using a Trace CDP-5300 compact CD printer, and was found to exhibit good image quality, dry time, and durability.

Comparative Example 3. A prior-art ink-receptive composition comprising 16.0 wt % poly[1,4-cyclohexylenedimethylene-co-2,2'-oxydiethylene (46/54) isophthalate-co-5-sodiosulfo-1,3-benzenedicarboxylate (82/18)] (obtained from Eastman Chemicals as AQ-55), 7.9 wt % poly(vinyl pyrrolidone) (PVP K-30 from International Specialty Products), 0.2 wt % poly(vinyl alcohol) (Airvol 350 from Air Products, Inc.), 1.5 wt % poly(methyl methacrylate-co-divinylbenzene) particles (average particle diameter : 15 μm , prepared by the Polymer Development Group at Eastman Kodak Co.), 0.1 wt % DF-75 (defoamer, from Air Products, Inc.), and 74.3 wt % distilled water was screen-printed over a writable 120-mm diameter CD as described in Example 1. It was found that the coating composition was too thin, that is, the viscosity was too low, and it leaked through the screen. A usable coating was not obtained.

Example 4. An ink-receptive composition comprising 5.64 wt % poly[1,4-cyclohexylenedimethylene-co-2,2'-oxydiethylene (46/54) isophthalate-co-5-sodiosulfo-1,3-benzenedicarboxylate (82/18)] (obtained from Eastman Chemicals as AQ-55), 2.4 wt % poly(vinyl pyrrolidone) (PVP K-30 from International Specialty Products), 0.08 wt % poly(vinyl alcohol) (Airvol 350 from Air Products, Inc.), 0.6 wt % poly(methyl methacrylate-co-divinylbenzene) particles (average particle diameter : 15 μm , prepared by the Polymer Development Group at Eastman Kodak Co.), 0.04 wt % DF-75 (defoamer, from Air Products, Inc.), 1.2 wt % Natrosol 99-250 H (thickener, from Aqualon Inc.), and 90 wt % distilled water was screen-printed over a writable 120-mm diameter CD as described in Example 1. It was found that the coating composition was screen-printable.

Example 5. Viscosity as a function of shear rate for the coating compositions described in Examples 1, 2, and 4 and comparative example 3 was measured using a Rheometrics Fluids Spectrometer with a cone and plane geometry. The instrument was set up with a plate diameter of 50 mm and a cone angle of 0.02 radian. The shear rate was varied from 10^{-1} to $10^{2.7} \text{ s}^{-1}$. Table 1 summarizes the pertinent data.

Table 1

Comparison of the rheological properties				
Example	η (poise) @ shear rate of 10^0 s^{-1}	A	Prior Art	Screen- Printable
1	160	-0.27	No	Yes
2	110	-0.17	No	Yes
3	0.36	-0.01	Yes	No
4	48	-0.51	No	Yes

This example shows that the ink-receptive compositions of the present invention which contain thickeners and which meet the requirements of viscosity ($\eta \geq 10$ poise at 10^0 s^{-1} and $A \leq -0.1$) are screen-printable, but the prior art compositions which do not contain thickeners and do not meet the rheological requirements are not screen-printable.

Claims

1. A screen-printable ink-receptive composition containing (a) a hydrophilic polymer composition and (b) a thickener and has (c) a viscosity of 10 to 1,000 poise at shear rates less than 10^0 s^{-1} and exhibits (d) a shear-thinning behavior defined by the following relationship:

$$\log(\text{viscosity}) = A [\log(\text{shear rate})]$$

wherein A represents (e) the slope of the line obtained by plotting $\log(\text{viscosity})$ against $\log(\text{shear rate})$ and has (f) a value of up to -0.1 when calculated over shear rates ranging from 10^0 to 10^2 s^{-1} .

2. A composition as claimed in claim 1 wherein the hydrophilic polymer composition comprises:

- (i) a poly(vinyl pyrrolidone);
- (ii) particles of a polyester ionomer poly[1,4-cyclohexylenedimethylene-co-2,2'-oxydiethylene isophthalate-co-5-sodiosulfo-1,3-benzenedicarboxylate; and
- (iii) a polyvinyl alcohol.

3. A composition as claimed in claim 2 comprising:
poly[1,4-cyclohexylenedimethylene-co-2,2'-oxydiethylene (46/54) isophthalate-co-5-sodiosulfo-1,3-benzenedicarboxylate (82/18)], poly(vinyl pyrrolidone) with a molecular weight of about 33,000, poly(vinyl alcohol), hydroxyethyl cellulose and water.
4. A composition as claimed in any one of the preceding claims comprising from 0.1 to 3.0 weight percent thickener.
5. A composition as claimed in claim 4 comprising 0.5 to 3.0 weight percent hydroxyethyl cellulose as the thickener.
6. A composition as claimed in claim 5 comprising 1.5 to 2.5 weight percent hydroxyethyl cellulose.
7. A composition as claimed in claim 6 also containing a defoamer.
8. A composition as claimed in claim 7 wherein the defoamer concentration is .01 to 0.15 weight percent.
9. A composition as claimed in claim 8 wherein the defoamer is silicone-free.
10. A composition as claimed in claim 2 wherein the poly(vinyl pyrrolidone) has a molecular weight of 10,000 to 500,000.
11. A composition as claimed in claim 10 wherein the poly(vinyl pyrrolidone) has a molecular weight of 10,000 to 100,000.
12. A method of screen printing an ink-receptive composition on a substrate comprising the steps of:
 - (a) providing a screen-printable ink receptive composition containing (i) a hydrophilic polymer and (ii) a thickener and has (iii) a viscosity of 10 to 1,000 poise at shear rates less than 10^6 s^{-1} and exhibits (iv) a shear-thinning behavior defined by the following relationship:

$$\log(\text{viscosity}) = A [\log(\text{shear rate})]$$
 wherein A represents (v) the slope of the line obtained by plotting $\log(\text{viscosity})$ against $\log(\text{shear rate})$ and has (vi) a value of up to -0.1 when calculated over shear rates ranging from 10^0 to 10^2 s^{-1} ;
 - (b) coating a fine meshed fabric screen with the composition provided in (a);
 - (c) placing the coated fabric screen over the substrate;
 - (d) filling the screen openings with the composition by passing an applicator over the surface of the fabric; and
 - (e) forcing the composition onto the surface of the substrate as a coating by passing an applicator under pressure over the surface of the fabric.
13. A process as claimed in claim 12 wherein the composition coated in step (e) is subjected to heating with an infrared lamp.
14. A process as claimed in claim 12 wherein the substrate is one surface of a writable CD.
15. A process as claimed in claim 12 wherein the substrate coated is a durable overcoat layer residing on one surface of a writable CD.
16. A composition as claimed in either of claims 1 and 2 comprising 10 to 60 wt % solids.
17. A composition as claimed in claim 16 comprising 30 to 40 wt % solids.
18. A composition as claimed in either of claims 16 and 17 being free of silicone-based oils and other uncrosslinked additives.




FIGURE 1



(11) EP 0 718 384 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
08.07.1998 Bulletin 1998/28

(43) Date of publication A2:
26.06.1996 Bulletin 1996/26

(21) Application number: 95203564.0

(22) Date of filing: 19.12.1995

(51) Int. Cl.⁶: B41M 1/30, B41M 1/12,
C09D 139/06, C08L 39/06,
G11B 7/26, B41M 5/00,
C09D 11/10

(84) Designated Contracting States:
DE FR GB

(30) Priority: 22.12.1994 US 362364

(71) Applicant: EASTMAN KODAK COMPANY
Rochester, New York 14650-2201 (US)

(72) Inventors:
• Krencski, Mary A.,
c/o Eastman Kodak Co.
Rochester, New York 14650-2201 (US)
• Swallow, Kevin J.,
c/o Eastman Kodak Co.
Rochester, New York 14650-2201 (US)

• Bugner, Douglas E.,
c/o Eastman Kodak Co.
Rochester, New York 14650-2201 (US)
• Amell, Alfred J.,
c/o Eastman Kodak Co.
Rochester, New York 14650-2201 (US)

(74) Representative:
Haile, Helen Cynthia et al
Kodak Limited
Patent Department
Headstone Drive
Harrow, Middlesex HA1 4TY (GB)

(54) Screen-printable ink-receptive compositions

(57) This invention is a screen-printable ink receptive composition. It contains (a) a hydrophilic polymer and (b) a thickener and has (c) a viscosity of 10 to 1,000 poise at shear rates less than 10^0 s^{-1} and exhibits (d) a shear-thinning behavior defined by the following relationship:

$$\log(\text{viscosity}) = A [\log(\text{shear rate})]$$

wherein A represents (e) the slope of the line obtained by plotting $\log(\text{viscosity})$ against $\log(\text{shear rate})$ and has (f) a value of up to -0.1 when calculated over shear rates ranging from 10^0 to 10^{-2} s^{-1} .




FIGURE 1

EP 0 718 384 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 95 20 3564

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	WO 93 03103 A (MINNESOTA MINING & MFG) 18 February 1993 * the whole document *	1,4	B41M1/30 B41M1/12 C09D139/06 C08L39/06 G11B7/26 B41M5/00 C09D11/10
A	EP 0 630 031 A (DU PONT) 21 December 1994 * examples 7-9 *	1,4,12,16	
D,A	EP 0 574 860 A (TAIYO YUDEN KK ; SONY CORP (JP)) 22 December 1993 * page 5, line 54 - page 6, line 13 *	1,4,7,12,14,15	
A	EP 0 337 705 A (SERICOL GROUP LTD) 18 October 1989 * page 2, line 21 - line 50 *	1,12	
A	US 4 180 491 A (KIM SAMUEL S ET AL) 25 December 1979 * the whole document *	1,12	
A	US 5 139 867 A (LIGHT WILLIAM A) 18 August 1992 * the whole document *	2	TECHNICAL FIELDS SEARCHED (Int.Cl.6) B41M C09D C08L G11B
E	US 5 599 649 A (SHINKAI MASAHIRO ET AL) 4 February 1997 * the whole document *	1,12,14-17	
P,X	& PATENT ABSTRACTS OF JAPAN vol. 096, no. 002, 29 February 1996 & JP 07 272441 A (TDK), 20 October 1995, * abstract *	1,12,14-17	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 15 May 1998	Examiner Holubov, C
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document		T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons & : member of the same patent family, corresponding document	

THIS PAGE BLANK (USPTO)